

Latex Free Dental Dam

Typical Properties

Tensile Strength
Modulus at 500% Extension
Elongation at Break
Tear Strength
12.0 MPa
1.3MPa
1100%
24 N/mm

THICKNESS

0.18mm/0.23mm Medium Gauge 0.23mm/0.28mm Heavy Gauge

+/- 10% Tolerance

Available as 6" x 6" (152mm x 152mm) or 5" x 5" (127mm x 127mm) squares or in rolls.

COLOURS

Light Blue

SAFETY INFORMATION

Composition:

Synthetic polyisoprene latex rubber plus essential processing chemicals and pigments.

Health Hazard:

Latex Free Dental Dam is generally considered non-hazardous and is safe for use by persons who know they are susceptible to Type I Allergies from natural latex. However, the product contains higher levels of dithiocarbamate than natural latex rubber and consequently may cause sensitisation by skin contact and give rise to Type IV Allergies. Persons who know they are susceptible to dithiocarbamates should avoid contact with polyisoprene. N-Nitrosamine by-products of dithiocarbamate are typically <10µg/kg (93/11/EEC limit for bottle teats) when tested by BSEN12868.

The physical properties above are typical values abstracted from tests based on ISO37 and ISO34:1

Four D Rubber Co. Ltd.

Units 11-15, Slack Lane, Heanor Gate Industrial Estate Heanor, Derbyshire, DE75 7SJ, England

Tel: +44 (0) 1773 763134 Email: info@fourdrubber.com Web: www.fourdrubber.com